

NZPP00011 Porter's Paints Aqua Enamel Gloss

Introduction

Part A
PF3-LINE

Description and Image

Porter's Aqua Enamel is a water based acrylic enamel that dries to an hardwearing finish that provides the benefits of an oil based enamel with none of the drawbacks. Excellent for exterior woodwork and trim areas as its high UV resistance ensures durability and longevity in a range of temperature and climatic conditions.

Features and Benefits

- Self levelling to minimise brush marks
- Interior & exterior
- Non-yellowing
- Excellent gloss retention
- Fast drying
- Low odour
- Easy to apply
- Hard wearing
- Fully washable
- High UV resistance
- Resists peeling and flaking

Uses

Interior and exterior. Ideal for doors, architraves, windows and trim. Excellent for exterior woodwork and trim areas as its high UV resistance ensures durability and longevity in a range of temperature and climatic conditions. Can be applied to most suitably prepared plasterboard, plaster, metal, wood, masonry and previously painted surfaces.

✓ Interior ✓ Exterior ✓ Doors, Windows & Trim

Precautions and Limitations

Do not apply in high humidity, below 10°C or above 30°C. Check colour before use.

Typical Properties			
Thinner Water			
Colour Available in a wide range of colors tinted from Standard, Mid, Deep, Clear, Red and Black bases or ask our colourist for your own custom colour.			
Acrylic Range Base:			
Ultra Flat:	Eggshell:	Low Sheen:	Aqua Satin Enamel:
Aqua Gloss Enamel: Standard Mid Deep Clear Black Red	Stone Paint Fine:	Stone Paint Coarse:	
Components 1	Number of Coats 2		
V.O.C. Level Between 87 g/L(Clear Base) and 107 g/L(Mid Base) Untinted.			
Touch Dry 1 hour (at 25 Deg C and 50% relative Humidity)			
Clean Up Water			
Clean Up Description Clean brushes and equipment with water. Do not pour paint down the drain. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Please confirm local requirements. For more information on responsible disposal of paint and packaging visit paintback.com.au or painttakeback.co.nz .			
Application Methods Airless Spray Brush Roller Short nap roller			
Application Conditions	Solids by Volume		
	<input type="text" value="34"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="71"/>	<input type="text" value="83"/>	<input type="text" value="77"/>
Dry Film Per Coat (microns)	<input type="text" value="24"/>	<input type="text" value="28"/>	<input type="text" value="26"/>
Recoat Time (min/hours)	<input type="text" value="3 hours"/>	<input type="text" value="indefinite"/>	<input type="text" value="3 hours"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="14"/>	<input type="text" value="12"/>	<input type="text" value="13"/>

Application Guide

Surface Preparation

New/unpainted substrates

Substrate should be a clean well-held surface free from loose material, dirt, grease, oil and mould. Dust down before proceeding. On bare surfaces such as new unpainted plasterboard sheeting, render, brick or timber, spot prime all joints and repaired areas with Porter's Universal Primer, then apply one coat of same to entire area. Touch dry 2 hours. Allow 6 hours dry time between coats and 24 hours dry time prior to the application of Aqua Enamel. On new unpainted fresh set plaster do not proceed until plaster has thoroughly set and has dried completely. Firstly, apply 1 coat Porter's Mineral Silicate Primer by brush or roller. Touch dry 20 minutes. Allow 2 hours dry time. Then apply by brush, roller or spray 1 coat Porter's Universal Primer. Touch dry 2 hours. Allow 6 hours dry time between coats and 24 hours dry time prior to the application of Aqua Enamel.

Previously painted substrates

When painting over a water-based acrylic paint, provided the surface is clean, sound and sanded to remove gloss, Porter's Aqua Enamel is self-priming and can be applied direct. All varnishes, polyurethanes or surfaces previously painted with oil-based enamel paint should be thoroughly sanded to remove gloss and to create a "keyed" surface. Loose, peeling or flaking paint must be made sound by scraping off loose paint. Fill nail holes and cracks with suitable filler, sand and dust off. Spot prime all joints and repaired areas with Porter's Universal Primer, then apply one coat of same to entire area. Touch dry 2 hours. Allow 6 hours dry time between coats and 24 hours dry time prior to the application of Aqua Enamel.

Complementary products

Porter's Universal Primer (coverage 10m² per litre) is also recommended. Gives a smoother overall result. Mineral Silicate Primer (coverage 10m² per litre) is recommended for priming new set plaster before undercoating.

Application Procedure and Equipment

Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point. Do not apply if the surface temperature is greater than 30°C or below 10°C, or likely to fall below 10°C during the application or drying period. Stir thoroughly prior to use. Apply two coats by brush, short nap roller or spray. Touch dry in 1 hour. Allow minimum 3 hours dry time between coats. Allow 8 hours dry time.

Health and Safety

SDS Number
DLXNZLEN001302

SDS Link
[View SDS Link](#)

Using Safety Precautions

Keep out of reach of children. Natural ventilation should be adequate under normal use conditions.

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Transport and Storage

Pack A
PF3-LINE

Size:

1 L & 4 L

Weight:

1.38 Kg & 5.31 Kg

Flash Point
NA

UN Number
NA

Dangerous Goods Class
Not classified as Dangerous Goods for transport by Road & Rail and Marine, Not classified as Dangerous Goods for transport by Air.

Package Group
NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.