

NZBG00025 Berger Gold Label Acrylic Gloss

Introduction

Product Code
67582358

Description and Image

Berger Gold Acrylic Gloss is a 100% acrylic paint for interior and exterior use.

Features and Benefits

- Water Based
- 100% Acrylic paint
- Ease of Application
- Same day recoat, easy clean up and low odour
- Excellent durability

Uses

Berger Gold Acrylic Gloss provides a long lasting gloss finish on suitably primed exterior and interior substrates.

Precautions and Limitations

Do not use at temperatures below 10C, or when the temperature of the surface may fall below 10C during the drying period. Avoid exposure to steam and condensation for 48 hours after application. Although the film is dry to touch in 30 minutes allow 7 days for film to fully cure before washing.
Tinted Colours: Ensure that the paint is thoroughly shaken and stirred immediately after addition of tinter to the can and again before use.

Performance Guide

Weather

Excellent resistance to weathering

Heat Resistance

Softens at temperatures over 70C

Water






Resists rain and condensation

Solvent

Sensitive to aromatic hydrocarbons and alcohols

Abrasion

Good resistance to abrasion

| Typical Properties | | | |
|---|--------------------------------------|---|---------------------------------|
| Gloss Level 50-70 at 60 degrees | Thinner Water | | |
| Colour White | | | |
| Components 1 | Number of Coats 2 | | |
| Toxicity Lead free. Dry film is non-toxic | V.O.C. Level < 65 g/L | | |
| Touch Dry 20 minutes | | | |
| Clean Up  Water | | | |
| Clean Up Description Clean all equipment with water | | | |
| Application Methods  Air Spray  Airless Spray  Brush  Roller | | | |
| Application Conditions | Solids by Volume | | |
| | <input type="text" value="38"/> | | |
| | Min | Max | Recommended |
| Wet Film Per Coat (microns) | <input type="text"/> | <input type="text"/> | <input type="text" value="71"/> |
| Dry Film Per Coat (microns) | <input type="text"/> | <input type="text"/> | <input type="text" value="27"/> |
| Recoat Time (min/hours) | <input type="text" value="2 hours"/> | <input type="text" value="Indefinite"/> | <input type="text"/> |
| Theoretical Spread Rate (m ² /L) | <input type="text"/> | <input type="text"/> | <input type="text" value="14"/> |

| Application Guide |
|---|
| <p>Surface Preparation</p> <p>All surfaces must be thoroughly cleaned and free of all loose dirt, dust, grease, loose or flaking paint, and loose surface plaster. Efflorescence on masonry or concrete surfaces must be treated. Any mould contamination needs to be removed. Flatten gloss surfaces by thoroughly sanding and wipe clean with a damp cloth, then apply primer, sealer or undercoat as required.</p> |
| <p>Application Procedure and Equipment</p> <p>Stir contents thoroughly before and during use with a broad flat stirrer using an upward action.</p> <p>Brush/Roller: Use a short nap roller. Pre-wet brushes and rollers with water before commencing application. Avoid excessive brushing or rolling back into the paint which has been drying for more than 3 minutes.</p> <p>Thinning not usually required. If necessary thin with up to 100 ml of water per litre to ease application.</p> <p>Airless/Conventional Spray: Suitable for application by all standard spray equipment. If necessary up to 100ml of water per litre may be added to aid atomisation.</p> <p>Brush, roller, conventional and airless spray</p> |

| Health and Safety | |
|---|---|
| SDS Number DLXNZLEN000730 | SDS Link View SDS Link |
| Using Safety Precautions For detailed information refer to the product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service offices | |
| Please refer to SDS Link. In case of emergency, please call 0800 220 770. | |

| Transport and Storage | |
|---|---|
| Pack A 67582358 | |
| Size: <input type="text" value="10 L"/> | Weight: <input type="text" value="13 kg"/> |
| Flash Point NA | UN Number NA |
| Dangerous Goods Class Not dangerous goods. No special transport requirements. | Package Group NA |

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.