

Metalshield® Premium Aluminium

Aluminium Flake Alkyd Enamel

- FEATURES**
- CONTAINS ALUMINIUM FLAKE
 - EASY TO APPLY
 - SINGLE PACK FINISH
 - RESISTS TEMPERATURES UP TO 200°C
 - EXCELLENT REFLECTIVE PROPERTIES
 - EXCELLENT WEATHERING RESISTANCE

- USES**
- METALSHIELD® PREMIUM ALUMINIUM is an alkyd enamel paint pigmented with metallic flake.
 - METALSHIELD® PREMIUM ALUMINIUM is easy to apply to a range of suitably primed metal substrates, such as mild steel, galvanised steel and aluminium, and offers a high metallic finish.
 - METALSHIELD® PREMIUM ALUMINIUM is typically used over conventional or epoxy metal primers on externals of metal tanks, corrugated metal roofing, gates, fences, ducting and miscellaneous steelwork.

RESISTANCE GUIDE

WEATHERABILITY	Very good compared to conventional alkyd enamels	SOLVENTS	Resists splash and spillage of aliphatic hydrocarbons
HEAT RESISTANCE	Up to 200°C dry heat	WATER	Resists rain and condensation. Not recommended for permanently damp or immersed exposure.
SALTS	Excellent resistance to neutral salt solutions	ALKALIS	Not recommended where fumes, splash or spillage may occur
ACIDS	Not recommended where fumes, splash or spillage may occur	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA

CLASSIFICATION	Heat resisting aluminium enamel		APPLICATION CONDITIONS			
FINISH	Metallic			Min	Max	
COLOUR	Bright Aluminium		Air Temp.	5°C	40°C	
COMPONENTS	One		Surface Temp.	5°C	40°C	
VOLUME SOLIDS	34%		Relative Humidity		85%	
VOC LEVEL	<490 g/L		Concrete Moisture			
FLASH POINT	-3°C		COATING THICKNESS (MICRONS)			
POT LIFE	Not applicable			Min	Max	Recommended
THINNER – BRUSH	965-H0010	Metalshield® Brush Thinner	Wet Film Per Coat (µm)	45	75	60
THINNER – SPRAY	965-H0009	Metalshield® Spray Thinner	Dry Film Per Coat (µm)	15	25	20
PRODUCT CODE	384-63008	Aluminium	SUITABLE SUBSTRATES	Suitably primed steel, aluminium and primed zinc coated steel		
			PRIMERS	Most Dulux® alkyd and two pack primers		
			TOPCOATS	Not applicable		
			APPLICATION METHODS	Air Spray, Airless Spray, Brush, Roller		

DRYING CHARACTERISTICS AT 20 µm DRY FILM THICKNESS

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max
25°C	50%	4-6 Hours	16 Hours	7 Days	16 Hours	Extended

The drying figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

SPREADING RATE

assuming no losses

17 square metres per litre equals 20 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

Metalshield® Premium Aluminium

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM		DFT (µm)
STEEL – NEW	Mild – Medium corrosivity (AS2312.1 Cat C2-4)	Power tool clean AS1627.2, Abrasive blast AS1627.4	1st Coat	Metalshield® High Build ZP Primer	50 µm
			2nd Coat	Metalshield® Premium Aluminium	20 µm
			3rd Coat	Metalshield® Premium Aluminium	20 µm
STEEL – NEW	Heat resistance only	Power tool clean AS1627.2, Abrasive blast AS1627.4	1st Coat	Metalshield® Premium Aluminium	20 µm
			2nd Coat	Metalshield® Premium Aluminium	20 µm
ALUMINIUM	Exterior/Interior	Clean, degrease and abrade surface	1st Coat	Luxepoxy® 4 White Primer	50 µm
			2nd Coat	Metalshield® Premium Aluminium	20 µm
			3rd Coat	Metalshield® Premium Aluminium	20 µm

NOTE: If application is by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity. For steelwork in moderate to severe corrosivity environments, a heavy duty protective coating system is recommended. Refer to a Dulux Protective Coatings Consultant.

SURFACE PREPARATION	Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Degrease with Gamlen CA 1 according to the data sheet and SDS. Abrasive blast clean to a minimum of AS1627.4 Class 2.5. Remove all dust. Steel where abrasive blast cleaning is not viable: Rust, millscale, oxide deposits and old paint films on metal surfaces must be removed by power tool cleaning according to AS1627.2 Class 2. Coating performance is proportional to the degree of surface preparation. Non-ferrous metals: Round off all sharp edges. Remove grease, oil and other contaminants in accordance with AS1627.1. Whip blast with fine non-metallic media to provide a key. Remove all dust with compressed air. Alternatively, degrease and abrade the surface with a non-metallic abrasive pad wetted with Gamlen CA 1 and water. Rinse thoroughly with fresh potable water.						
APPLICATION	Mix each can thoroughly using a power mixer until the contents are uniform. Remix thoroughly before and occasionally during application to prevent settling.						
APPLICATION EQUIPMENT	Airless Spray: Standard airless spray equipment such as a Graco Xtreme 30:1 with a fluid tip of 13-15 thou (0.33-0.38mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Thinning is not usually required but up to 50 ml/litre of Metalshield® Spray Thinner (965-H0009) may be added to aid application.						
	Tip Orifice		Atomising Pressure		Material Hose ID		Pump Manifold Filter
	13-15 thou (0.33-0.38mm)						
	Conventional Spray: Thin up to 50 ml/litre with Metalshield® Spray Thinner (965-H0009) to aid atomisation. Add only enough thinner to achieve atomisation. Apply in multiple wet coats overlapping each pass 50%.						
	Gun	Fluid Tip	Air Cap	Air Hose ID	Material Hose ID	Atomising Pressure	Material Pressure
	Graco AirPro	1.4mm	239542			380-410 kPa (55-60 p.s.i.)	70-100 kPa (10-15 p.s.i.)
	Roller: Apply even coats of the mixed material to the prepared surface. Thin if necessary with up to 50 ml/litre with Metalshield® Brush Thinner (965-H0010) to aid application. When rolling additional coats may be required to attain the specified thickness.						
	Brush: Apply even coats of the mixed material to the prepared surface. Thin if necessary with up to 50 ml/litre with Metalshield® Brush Thinner (965-H0010) to aid application. When brushing additional coats may be required to attain the specified thickness.						
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the written consent of Dulux® Australia. Do not apply at temperatures below 5°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Do not overcoat before the minimum overcoat interval or wrinkling may occur. NOTE: This product must not be directly applied on galvanised iron or zinc rich coatings.						
CLEAN UP	Clean all equipment with Metalshield® Spray Thinner (965-H0009) immediately after use.						
OVERCOATING	Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 - 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating.						
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (132377) or www.duluxprotectivecoatings.com.au						
	Product Line Shade, Product Name, and SDS Number				SDS Link		
	384-63008, METALSHIELD PREMIUM ALUMINIUM, DLXGHSN001368				View SDS Link		
STORAGE	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.						
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 must be worn while handling and using. Always wash hands before smoking, eating, drinking or using the toilet.						

Metalshield® Premium Aluminium

USING	Use with good ventilation and avoid inhalation of spray mists and fumes. When spraying, wear combined organic vapour/particulate respirator. Users must always comply with their respective State Spray Painting Regulations at all times
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO ₂ or dry chemical powder. On burning will emit toxic fumes.
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

COMPANY INFORMATION		PACKAGING, TRANSPORT AND STORAGE			
Dulux Protective Coatings is a division of		PACKAGING Available in 1 litre and 4 litre cans			
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427		TRANSPORTATION WEIGHT 1.08 kg/litre			
DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118		DANGEROUS GOODS Part A: Class 3 UN 1263 Part B: N/A N/A			

© Dulux, Luxepoxy and Metalshield are registered trade marks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.