

## NZCA00022 Cabot's Cabothane Clear Oil Based Gloss

### Introduction

Part A  
864 82031

### Description and Image

**Cabot's Cabothane Clear Oil Based** is a highly durable, hard wearing varnish suitable for use on timber doors, windows, trim and furniture. It is resistant to chemicals, oils, solvents and withstands abrasion, scuffing and scratching. It also contains UV absorbers, meaning it is Interior/Exterior durable and protects surfaces such as windows and doors that are exposed to sunlight. Cabot's Cabothane Clear also performs as a clear topcoat over Cabot's Interior Stain Oil Based.



### Features and Benefits

- High durability.
- Resists stains & scratches.
- Enhances timber grain.
- Reduced odour & 6 hour recoat.
- UV resistant.
- Highly durable polyurethane coating to protect timber for longer.
- Cabothane is a tough coating that resists chemicals, abrasion, scuffing and scratching.
- Enhances the natural colour of the timber grain.
- Cabothane has reduced odour and can be recoated in just 6 hours.
- UV resistant to protect surfaces such as windows and doors which are exposed to sunlight.



### Uses

Timber doors, windows, trim and furniture.

### Precautions and Limitations

Do not apply this product in temperatures below 10°C or above 35°C, or when rain or heavy dew is expected during the drying period. If using outside in hot temperatures, do not apply in direct sunlight. Cool the timber by lightly dampening with water and coat in the shade.  
**Note** for surfaces subject to extreme UV exposure, use Cabot's Exterior Clear.

Performance Guide	
Weather <b>Interior and Exterior use.</b>	Salt <b>Unaffected by splash or spillage.</b>
Heat Resistance <b>Up to 100C.</b>	Water <b>Good.</b>
Solvent <b>Resists alcohol and hydrocarbons.</b>	Abrasion <b>Moderate.</b>
Acid <b>Suitable for dilute splash.</b>	Alkali <b>Suitable for dilute splash.</b>

Typical Properties																													
Gloss Level <b>Gloss</b>																													
Colour <b>Clear</b>																													
Components <b>1</b>	Number of Coats <b>3</b>																												
Toxicity <b>Lead free</b>	V.O.C. Level <b>&lt; 455g/L</b>																												
Touch Dry <b>2 hours</b>																													
Clean Up Description Mineral turpentine. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																													
Application Methods  <b>Brush</b>  <b>Spray</b>																													
Application Conditions	<table border="1"> <thead> <tr> <th colspan="2">Solids by Volume</th> <th colspan="2">Recommended</th> </tr> <tr> <th>Min</th> <th>Max</th> <th colspan="2"></th> </tr> </thead> <tbody> <tr> <td colspan="2"><input type="text" value="43"/></td> <td colspan="2"></td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td><input type="text"/></td> <td colspan="2"><input type="text" value="63"/></td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td><input type="text"/></td> <td colspan="2"><input type="text" value="27"/></td> </tr> <tr> <td>Recoat Time (min/hours)</td> <td><input type="text" value="6 hours"/></td> <td colspan="2"><input type="text"/></td> </tr> <tr> <td>Theoretical Spread Rate (m<sup>2</sup>/L)</td> <td><input type="text"/></td> <td colspan="2"><input type="text" value="16"/></td> </tr> </tbody> </table>	Solids by Volume		Recommended		Min	Max			<input type="text" value="43"/>				Wet Film Per Coat (microns)	<input type="text"/>	<input type="text" value="63"/>		Dry Film Per Coat (microns)	<input type="text"/>	<input type="text" value="27"/>		Recoat Time (min/hours)	<input type="text" value="6 hours"/>	<input type="text"/>		Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text"/>	<input type="text" value="16"/>	
Solids by Volume		Recommended																											
Min	Max																												
<input type="text" value="43"/>																													
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text" value="63"/>																											
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text" value="27"/>																											
Recoat Time (min/hours)	<input type="text" value="6 hours"/>	<input type="text"/>																											
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text"/>	<input type="text" value="16"/>																											
Typical Property Notes <b>Spreading rate</b> Approximately 16 square metres per litre depending on the porosity and condition of the timber.  <b>Drying and re-coat time</b> All timings quoted at 25C and 50% humidity. Cooler or humid conditions may require longer.																													

**Application Guide**

Surface Preparation

**Note** fill nail holes, cracks and other defects with Cabot's Wood Tone Putty after applying the first coat of this product for accurate colour matching. Remove stains, dirt, wax, grease and oil with mineral turpentine. Remove any polish with a suitable polish remover.

**Bare interior timber**

Sand the surface smooth using 180 - 240 grit sandpaper. Sand only in the direction of the grain. Remove all traces of sanding dust.

**Bare exterior timber**

Allow timber to weather for 4 - 6 weeks. For exterior surfaces only, clean with Cabot's Deck Clean following label instructions.

**Previously coated interior timber**

Thoroughly clean the surface with Cabot's Floor Clean and allow to dry. Sand with 180 - 240 grit sandpaper and remove all traces of sanding dust. Apply one coat to a small test area. Allow to dry for 6 hours. Press sticky tape firmly to the surface and pull off quickly. If the coating comes off, sand back to bare timber. If coating adheres well, sand the entire area with 180 - 240 grit paper for good adhesion, remove dust, then follow application instructions.

**previously coated exterior timber**

For best results, remove back to bare timber using a paint stripper, or sanding. For exterior surfaces only, clean with Cabot's Deck Clean following label instructions.

Application Procedure and Equipment

**Note** do not shake can. Stir thoroughly with a broad flat paddle before and during use. Apply with a good quality brush or spray gun. If spraying, back brushing is recommended. If brushing, always brush in the direction of the grain. Allow to dry for a minimum of 6 hours then lightly sand using 240 grit paper. Remove all sanding dust. Apply the 2nd & 3rd coats as above, lightly sanding with 240 grit paper between each coat.

**Staining bare interior timber**

If timber is to be stained, apply one coat of Cabot's Interior Stain Oil Based or Stain & Varnish Oil Based following label instructions. For Cabot's Interior Stain Oil Based only: Allow stain to dry for 8 hours and apply 3 coats of Cabothane Clear following application procedure above.

**Note** to stain previously coated timber, sand back to bare timber before staining.

**Hints** Cabot's Cabothane Clear is not suitable for:

- previously wax coated finishes
- walk-on areas
- extreme UV exposure
- broad wall application

For surfaces subject to extreme UV exposure, use Cabot's Exterior Clear.

**Health and Safety**

SDS Number  
**13661263**

SDS Link  
[View SDS Link](#)

Using Safety Precautions

**Risk**

Flammable. Irritating to skin. Avoid contact with skin and eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying. If painting large areas wear an organic vapour respirator. This paint is flammable, so eliminate any sources of ignition. Do not smoke.

**Please refer to SDS Link. In case of emergency, please call 0800 220 770.**

**Transport and Storage**

Line Shade/Pack A

**864 82031**

Size:

Weight:

4L 1L 500ml 250ml

4.1Kg 1.1Kg 0.6Kg 0.3Kg

**Please refer to the Safety Data Sheet for full safety, health and transportation information.**

**Disclaimer**

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.