

NZPR00071 Dulux Professional Enamel High Gloss

Introduction

Part A
307 LINE

Approvals
APAS 0015/1 (White, Deep & Ultra Deep Base only)

Description and Image

Dulux Professional High Gloss Enamel is a high quality interior/exterior high gloss oil based enamel with high opacity, high film build, excellent durability, gloss retention and resistance to chalking.

Features and Benefits

- Interior & Exterior Finish
- High Film Build & Opacity
- Excellent Flow & Levelling
- Excellent durability - lasts longer, less frequent repaints
- Needs only one coat on prepared surfaces - saves application time
- Ideal for mirror finishing & flood coating

Uses

Dulux Professional High Gloss Enamel is a hard wearing high gloss finish for suitably prepared interior and exterior timber, masonry and metal surfaces. Ideal for mirror finishing and flood coating.

✓ **Interior** ✓ **Exterior** ✓ **Doors, Windows & Trim**

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.

Check adhesion of old paint by cutting an 'X' through the film with a razor blade or trimming knife, press cellulose tape firmly across the cut and rip it off. If the old paint comes off with the tape it should be removed before repainting.

Do not apply if the surface temperature is below 10C or conditions indicate it will fall below 10C during the drying period.

Do not apply externally when weather is doubtful as frost, rain or dew on the uncured film may result in complete loss of gloss or patchiness and impair durability.

All enamels will yellow with age. This can be accelerated by darkness, heat and exposure to ammonia from freshly painted acrylic paints and some cleaning agents, particularly during the drying period.

Performance Guide

Weather

Very good resistance to weathering. May chalk after several years exposure.

Heat Resistance

Up to 120C. Premature yellowing & embrittlement will occur if film is subjected to continuous heat

Water

Resists prolonged exposure to rain and condensation.

Solvent

Resists alcohol & hydrocarbons. Film is liable to attack from any other strong solvents.

Abrasion

Excellent resistance to abrasion.

Typical Properties			
Gloss Level 85-95 at 60 degrees.	Thinner Mineral Turpentine		
Colour Can be machine tinted to a comprehensive pastel and medium depth colour range.			
Components 1			
Toxicity Lead free. Dry film is non-toxic and conforms to AS1647 Part 3.	V.O.C. Level < 420g/L untinted		
Touch Dry 4 Hours			
Clean Up  Thinner			
Clean Up Description Thoroughly wash brushes in mineral turpentine.			
Application Methods  Air Spray  Airless Spray  Brush  Roller			
Application Conditions	Solids by Volume 51		
Wet Film Per Coat (microns)	Min 63	Max 63	Recommended 63
Dry Film Per Coat (microns)	32	32	32
Recoat Time (min/hours)	16 Hours	Indefinite	
Theoretical Spread Rate (m ² /L)	16	16	16

Application Guide			
Surface Preparation			
Remove grease, oil, etc. by washing with a commercial paint cleaner. Thoroughly rinse and allow to dry. Acid and alkali contamination should be removed by thorough rinsing with clean water. Efflorescence or mould on plaster, masonry or timber surfaces must be treated. Rust, millscale, oxide deposits, loose or flaking paint or other foreign material on metal surfaces should be removed in accordance with the requirements of the chosen system, then apply primer, sealer or undercoat as required.			
Application Procedure and Equipment			
Brush, roller, conventional and airless spray. Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action.			
Brush/Roller: Apply one or two full coats to the prepared surface. Reduce if necessary with up to 50 ml per litre of mineral turpentine. Airless/Conventional Spray: Suitable for application by all standard spray equipment. If necessary thin with spraying thinner with up to 30 ml per litre for airless and 125 ml per litre conventional spray.			

Health and Safety

SDS Number DLXNZLEN000233	SDS Link View SDS Link
-------------------------------------	---

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Transport and Storage

Pack A 307 LINE	Size: 4 Litre 10 Litre	Weight: 5.1Kg 12.6Kg
Flash Point >23C	UN Number 1263	
Dangerous Goods Class 3	Package Group III	

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.