

NZDU04275 Dulux Concrete & Paving Clear Protective Sealer Satin

Description and Image

Dulux Concrete & Paving Clear Protective Sealer is ideal for enhancing the natural look of surfaces in high traffic areas. This clear sealer is non-yellowing, easy to apply, and suitable for protecting paths, steps, driveways and garage floors.

SLOPED SURFACES: Add the Dulux Concrete & Paving Anti-Slip Additive to gain a slip resistant surface. Do not apply to gradients greater than 1:8, even with the use of the anti-slip additive, due to slip risk.



Features and Benefits

- Protects & rejuvenates the look of the surface
- Easy to apply
- Non-yellowing
- Ideal for use on garage floors and driveways
- Resists grease and oil stains
- Easy to clean

Uses

Ideal for stone and paving paths, steps, garage floors and driveways where you want to protect the surface while enhancing the natural look.

Suitable substrates: Concrete (including coloured, pattern sealed and stencilled concrete), pavers, natural and engineered stone, sandstone, exposed aggregate and pebbles, brick, unglazed terracotta tiles, limestone and porous tiles.

ONLY USE IN WELL VENTILATED SPACES.

✓ Interior ✓ Exterior

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.

Do Not paint at surface temperatures below 10°C or when the temperature of surface may fall below 10°C during the drying period.

Do Not paint at surface temperatures above 35°C or when the temperature may exceed 35°C during the drying period.

Do Not apply to pavement surfaces that have a gradient greater than 1:8 or slope of 7 degrees.

For surfaces greater than 1:8 or 7 degrees please refer to Dulux Help and Advice for assistance.

Preparation of the surface is essential for the project success. All grease, oil, mould, and dirt contamination must be removed, or the primer will not adhere and will peel or flake off.

Avoid exposure to rain or water for a minimum of 1 hour after application.

Although film is generally dry to touch in 30 minutes, allow 24 hours before light foot traffic and 5 days before vehicular traffic.

New Concrete:

- For newly poured concrete, it is recommended to allow a minimum of 4 weeks for proper curing before proceeding with surface preparation and painting. The curing process is a crucial stage in concrete development, where the concrete gains strength and durability over time. Failure to allow sufficient curing time can result in a weak and porous concrete surface, leading to adhesion issues and premature coating failure. Additionally, if the concrete is not fully cured, moisture can still be present within the surface, which can cause problems with coating adhesion and result in bubbling, blistering or peeling of the coating.

Use of Dulux Concrete & Paving Prep System:

- If the concrete surface is bare or new, use Dulux Concrete & Paving Bare Etch & Clean (52ZD0198)
- If the concrete surface is pre-painted or other sealed surfaces, use Dulux Concrete & Paving Sealed Surface Cleaner (52ZD0184)

Important: Do Not Use Dulux Concrete & Paving Bare Concrete Primer (52ZD0183) and Dulux Concrete & Paving Sealed Surface Primer (52ZD0200) prior to application of Dulux Concrete & Paving Clear Protective Sealers (32QD0175).

Adherence to minimum recoat times:

- It is critical to strictly adhere to the minimum recoat times to prevent any unintended reduction in gloss resulting from an early recoat.
- Prior to applying the topcoat, ensure to mask up any areas that do not require coating using a high-quality masking tape. It is crucial to ensure that all areas are appropriately covered, as it will prove challenging to remove the coating once it has cured.

Important: before applying Dulux Concrete & Paving Clear Protective Sealer Satin, it is critical to ensure that the surface is fully dried, and the moisture level is below 10%.

Dry test:

- To check the moisture in the concrete, cut a 300MM x 300MM sheet of plastic such as a heavy-duty garbage bag or cling wrap. Place it onto the concrete surface.
- Use a duct tape or masking tape to secure the edges of the plastic sheet, and allow it to sit undisturbed for 2 hours.
- After 2 hours, remove the plastic and check for water droplets on the underside of the plastic or any signs of the concrete appearing darker in colour, which indicates the presence of moisture in the concrete.
- If moisture is present, it is not recommended to apply any solvent-based coating on the surface.
- If the moisture is a result of recent etching and cleaning of the concrete, wait for at least 24 hours (no exposure to rain or water) before performing the 'dry test' again to ensure that the concrete has sufficiently dried.

Product Application:

For improved slip resistance, especially in wet areas, pool surrounds, and steps, it is crucial to incorporate Dulux Concrete & Paving Anti slip Additive into the surface.

Do Not Use Dulux Concrete & Paving Clear Protective Sealer Satin (32QD0175) on any of Dulux Concrete & Paving water-based topcoats and vice versa.

The Dulux Concrete & Paving water-based topcoats are:

Dulux Concrete & Paving Coloured Sealer (52RD0152, 52ND0152)

Dulux Concrete & Paving Crushed Pebble Effect (52WD0165, 52WD0173)

Dulux Concrete & Paving Super Grip (52VD0153)

Return to use:

It is important to apply the recommended number of coats to ensure proper coverage and achieve adequate film builds.

- After 24 hours – the coated surface can accommodate light usage, such as walking. However, it is important to avoid placing any objects on the surface and to be cautious of exposure to water and other liquid materials.
- After 5 days – the surface can sustain general use, including driving and parking of vehicles.




FAQ Reference

<https://www.dulux.com.nz/products/concrete-paving/faq>.

Performance Guide

Weather Designed for interior and exterior use.	Salt Resistant against salt.
Heat Resistance Resistant to heat up to 80oC.	Water Resistant against water. This is not a waterproofing coating. The coating should not be exposed to ponded water situation.
Abrasion Good wet and dry burnish resistance and stain resistance.	
Acid Resistant against mild acids.	Alkali Resistant against mild alkalis.

Typical Properties

Gloss Level SATIN	Thinner DO NOT THIN. Product is ready to use.
Colour Clear.	
Components 1	Number of Coats 2 coats or more
Toxicity Lead free. Dry film is non-toxic	V.O.C. Level 689g/L
Shelf Life 2 years minimum from Date of Manufacture, in an unopened container.	
Sanding Properties Not applicable.	Mixing Ratio Not applicable.
Pot Life Not applicable.	Touch Dry Not applicable.
Clean Up  Thinner	
Application Methods  Brush  Roller	

Application Conditions	Solids by Volume		
	<input type="text" value="24.5"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="164"/>	<input type="text" value="164"/>	<input type="text" value="164"/>
Dry Film Per Coat (microns)	<input type="text" value="41"/>	<input type="text" value="41"/>	<input type="text" value="41"/>
Recoat Time (min/hours)	<input type="text" value="120"/>	<input type="text" value="120"/>	<input type="text" value="120"/>

Theoretical Spread Rate (m²/L)

5.98

5.98

5.98

Typical Property Notes
Touch Dry: 30 minutes.
Recoat: 2 hours.

Application Guide

Surface Preparation

Dulux Concrete & Paving Clear Protective Sealer Satin requires a clean surface to adhere. Do Not Use Dulux Concrete & Paving Bare Concrete Primer (52ZD0183) and Dulux Concrete & Paving Sealed Surface Primer (52ZD0200) prior to application of Dulux Concrete & Paving Clear Protective Sealers (32QD0175).

Preparation of the surface is essential for the project success. All grease, oil, mould, and dirt contamination must be removed, or the paint will not adhere and will peel or flake off.

All new and old bare concretes:

1. New concrete surfaces should be allowed to cure for at least 28 days prior to painting.
2. Pressure wash the surface (use a 1200psi or higher-pressure machine) to remove dirt dust, algae, mould and other contaminants as well as possible.
3. Apply Dulux Concrete & Paving Bare Concrete Etch & Clean (52ZD0198) using a plastic watering can evenly apply, before scrubbing into the surface. (NB: acid alone will not clean the concrete, nor will it break down oils and silicone residue. Acid only works by reacting with the alkaline salts in the concrete. If the concrete is covered with these residues, the acid will likely just sit there and do nothing. Dulux Concrete & Paving Bare Concrete Etch & Clean contains both acid and surfactants. The latter are designed to help remove any oily residues in the surface)
4. Allow Dulux Concrete & Paving Bare Concrete Etch & Clean to remain on the surface for 10-15 minutes even though most reaction (seen as bubbling/fizzy reaction) will likely subside after a couple of minutes. Ensure that the surface does not dry out. Some reaction products from the acid may form insoluble residue. If this occurs and the surface dries these residues will be very hard to remove
5. Power wash the surface to remove all residues released.
6. Allow the cleaned surface to fully dry and the surface moisture level must be below 10% before the application of Dulux Concrete & Paving Clear Protective Sealer Satin.

Previously painted concrete surfaces & non-porous surfaces:

1. Pressure wash the surface (use a 1200psi or higher-pressure machine) to remove dirt dust, algae, mould and other contaminants as well as possible.
2. Apply Dulux Concrete & Paving Sealed Surface Cleaner (52ZD0184) using a plastic watering can evenly apply, before scrubbing into the surface. Allow Dulux Concrete & Paving Sealed Surface Cleaner to remain on the surface for 10-15 minutes even though most reaction (seen as bubbling/fizzy reaction) will likely subside after a couple of minutes. Ensure that the surface does not dry out.
3. Power wash the surface to remove all residues released.
4. Allow the cleaned surface to fully dry and the surface moisture level must be below 10% before the application of Dulux Concrete & Paving Clear Protective Sealer Satin.

Combination surfaces (bare surface and sealed surface are present):

1. Pressure wash the surface (use a 1200psi or higher-pressure machine) to remove dirt dust, algae, mould and other contaminants as well as possible
2. Apply Dulux Concrete & Paving Sealed Surface Cleaner (52ZD0184) using a plastic watering can evenly apply, before scrubbing into the surface. Allow Dulux Concrete & Paving Sealed Surface Cleaner to remain on the surface for 10-15 minutes even though most reaction (seen as bubbling/fizzy reaction) will likely subside after a couple of minutes. Ensure that the surface does not dry out.
3. Power wash the surface to remove all residues released.
4. Apply Dulux Concrete & Paving Bare Concrete Etch & Clean (52ZD0198) using a plastic watering can, to bare patches of concrete. Allow Dulux Concrete & Paving Bare Concrete Etch & Clean to remain on the surface for 10-15 minutes even though most reaction (seen as bubbling/fizzy reaction) will likely subside after a couple of minutes. Ensure that the surface does not dry out. Some reaction products from the acid may form insoluble residue. If this occurs and the surface dries these residues will be very hard to remove.
5. Power wash the surface to remove all residues released.
6. Allow the cleaned surface to fully dry and the surface moisture level must be below 10% before the application of Dulux Concrete & Paving Clear Protective Sealer Satin.

Application Procedure and Equipment

Application:

Brush (50-65mm high quality angled Sash Cutter brush) and roller (15mm nap, 230mm or 270mm wide microfibre roller)
Stir thoroughly before and during use.

1. Mask all adjacent surfaces to prevent product contaminating areas that are not needed for the application.
2. Stir well before and during application with a broad, flat paddle using an up and down scooping action.
3. Use a brush to apply to any edges and hard-to-reach places.
4. Then, use a roller to apply 1st coat of Dulux Concrete & Paving Clear Protective Sealer Satin evenly across the surface. Work in small sections, slightly overlap the previous section to minimize raised edges

5. Lay off. Once section is coated, gently go over the surface in the same direction with an unloaded roller using minimal pressure. This will give a smooth consistent finish. Using poor quality or worn rollers can affect the final finish achieved.
6. Allow to fully dry before applying the 2nd coat.
7. Apply 2nd coat by repeating steps 2-5.

Tip: for rough concrete with peaks and dips, you may find that the paint is difficult to apply in the dips. On the 1st coat try using the edges of the roller or a paint brush to work the paint into dips. Allow too fully dry.

Do Not Use Dulux Concrete & Paving Clear Protective Sealer Satin (32QD0175) on any of Dulux Concrete & Paving water-based topcoats and vice versa. The Dulux Concrete & Paving water-based topcoats are: Dulux Concrete & Paving Coloured Sealer (52RD0152, 52ND0152), Dulux Concrete & Paving Crushed Pebble Effect (52WD0165, 52WD0173), Dulux Concrete & Paving Super Grip (52VD0153).

Application (Include Dulux Concrete & Paving Anti-slip Additive):

For improved slip resistance, especially in wet areas, pool surrounds, and steps, it is crucial to incorporate Dulux Concrete & Paving Anti-slip Additive (52ZD0182) into the surface.

For 10L Dulux Concrete & Paving Clear Protective Sealer Satin, stir in 300g of Dulux Concrete & Paving Anti-slip Additive (52ZD0182-300G).
For 4L Dulux Concrete & Paving Clear Protective Sealer Satin, stir in 120g of Dulux Concrete & Paving Anti-slip Additive (52ZD0182-120G).
If less paint is required, add 30g of Dulux Concrete & Paving Anti-slip Additive to PER LITRE of Dulux Concrete & Paving Clear Protective Sealer Satin.

1. Before applying Dulux Concrete & Paving Clear Protective Sealer Satin, mix in the required amount of Dulux Concrete & Paving Anti-slip additive.
2. Mask all adjacent surfaces to prevent product contaminating areas that are not needed for the application.
3. Stir well before and during application with a broad, flat paddle using an up and down scooping action.
4. Use a brush to apply to any edges and hard-to-reach places.
5. Then, use a roller to apply 1st coat of Dulux Concrete & Paving Clear Protective Sealer Satin (including the anti-slip additive) evenly across the surface. Work in small sections, slightly overlap the previous section to minimize raised edges.
6. Lay off. Once section is coated, gently go over the surface in the same direction with an unloaded roller using minimal pressure. This will give a smooth consistent finish. Using poor quality or worn rollers can affect the final finish achieved.
7. Allow to fully dry before applying the 2nd coat.
8. Apply 2nd coat by repeating steps 3-6

Health and Safety

SDS Number
DLX004248

SDS Link
[View SDS Link](#)

Using Safety Precautions

Wear overalls, safety glasses and impervious gloves.

Available information suggests that gloves made from nitrile rubber should be suitable for intermittent contact. However, due to variation in glove construction and local conditions, the user should make a final assessment. Always wash hands before smoking, eating, drinking, or using the toilet. Wash contaminated clothing and other protective equipment before storing or re-using.

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Transport and Storage	
Pack A 1	
Size: 4L, 10L	Weight: 4.093KG, 10.062KG
Flash Point 27 (XYLENE)	UN Number 1263
Dangerous Goods Class Classified as Dangerous Goods Class 3	Package Group Not Applicable

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.co.nz. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.