NZDU00454 Dulux Metalshield Epoxy Enamel Satin

Introduction

Product Code
31B-Line

Description and Image

Dulux Metalshield Epoxy Enamel Satin is a heavy duty topcoat that is ideal for protecting and decorating metal surfaces. Dulux Metalshield Epoxy Enamel provides a convenient solution where no primer is required over new bare steel, wrought iron or pre-painted metal surfaces. Use in combination with Metalshield primers for industrial strength metal protection.

Features and Benefits

- No primer required for new bare steel and wrought iron or pre-painted metal surfaces
- Interior/Exterior
- Protects against rust and corrosion
- Ideal for metal gates, fences, outdoor furniture, gutters, downpipes and railings
- Satin finish
- Resists knocks and scratches
- Can be tinted to an extensive range of Dulux colours

Uses

Use DULUX Metalshield Epoxy Enamel Satin as a topcoat for suitably prepared metal substrates.

Performance Guide

Weather **Good weather resistance, may show tendency to chalk after several years.**	Salt **Resists salt spray**
Heat Resistance **Up to 120°C. Premature yellowing and embrittlement will occur if film subjected to continuous heat.**	Water **Resists rain and condensation for prolonged periods**
Solvent **Resists alcohol and aliphatic hycarbons. Film is liable to attack from other strong solvents**	Abrasion **Excellent resistance to abrasion**

Typical Properties	
Gloss Level **30 - 50 at 60 degrees**	Thinner **Metalshield Brush Thinner**
Colour **Tintable with Dulux Decorama Tinters**	
Dulux Colour Base ✓ **Black**	
Components **1**	Number of Coats **2**
Toxicity **Lead Free. Dry film is non toxic**	V.O.C. Level **<450g/L**
Clean Up **Thinner**	
Clean Up Description Clean equipment with Metalshield Brush Thinner	
Application Methods **Air Spray** **Airless Spray** **Brush** **Roller**	

Application Conditions

Solids by Volume: 45

	Min	Max	Recommended
Wet Film Per Coat (microns)			65
Dry Film Per Coat (microns)			34
Recoat Time (min/hours)	24 hours	Indefinite	24 hours
Theoretical Spread Rate (m²/L)			14.71

Application Guide

Surface Preparation

Pre-painted metal surfaces: Scrap off all loose and flaking paint. Sand all surfaes to a flat finish. Dust off. If previously painted metal surface is in good condition then no primer is required. Treat any bare metal as below.
Aged/Lightly rusted surfaces: Remove any rust by scraping, sanding or wire brushing. Wipe surface with Metalshield Brush thinner to remove any residual grease, oils and dirt. Once dry, apply 1coat of Metalshield All Surface Primer.
New Bare Steel and Wrought Iron: Wipe surface with Metalshield Brush Thinner to remove any residual grease, oils and dirt. Then abrade with a Scotch-Brite® Pad. Wipe clean.
Galvanised Iron, Zincalume®: Clean surface with sugar soap and a Scotch-Brite® Pad to remove any grease, oils and dirt. Rinse with clean water. Once dry, apply 1 coat of Metalshield RFU Etch Primer.
Aluminium, Copper, Brass, Stainless Steel: Clean surface with sugar soap and a Scotch-Brite® Pad to remove any grease, oils and dirt. Rinse with clean water. Once dry, apply 1 coat of Metalshield All Surface Primer.
Ensure the surface has thoroughly dried prior to application. This product is ideal for domestic applications. For highly corrosive environments and for commercial applications refer to duspec.com.au or duspec.co.nz for appropriate specifications.

Application Procedure and Equipment

Brush, roller, conventional or airless spray
Stir contents thoroughly before and during use with a broad flat stirrer, using an upward lifting action.
Brush/Roller: Apply two full coats to the prepared surface. Thinning is not usually required. Airless/Conventional Spray: Suitable for application by all standard spray equipment. If necessary thin with up to 100 ml/litre of Metalshield Spray Thinner or Metalshield Brush Thinner.
Application and drying temperatures must be above 10C. Drying times at 25C and 50% RH: Touch Dry 4 Hours, Re-coat 24 Hours.
Note : Thinning can reduce the rust inhibiting performance of Metalshield Epoxy Enamel.

Health and Safety

SDS Number	SDS Link
23008	

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Transport and Storage

Pack A

31B-Line

Size:	Weight:
500mL 1L 4L	**0.8 Kg 1.3 Kg 4.6Kg**

Flash Point	UN Number
>23°C	**1263**
Dangerous Goods Class	Package Group
3	**II**

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.