

NZDU00311 Dulux Renovation Range Clear Satin

Introduction

Part A
51MD0065-1L

Part B
51XD0100-unit

Description and Image

Dulux® Renovation Range Clear Coat is a revolutionary, water based interior coating that is designed to add a layer of protection to the Dulux Renovation Range topcoats. It is easy to apply, providing a durable, chip, stain resistant, washable finish that you can achieve yourself.



Features and Benefits

- Waterbased & easy to apply
- For benchtops & tiles
- Durable & chip resistant
- Washable
- For use with Dulux Renovation Range products

Uses

Dulux Renovation Range Clear Coats can be used on kitchen, bathroom and laundry surfaces. To be used as final protection layer. Not suitable for floors.

✓ **Interior**

Precautions and Limitations

Under cooler or humid conditions allow longer drying times. Surface temperature must be above 10°C during application and drying. Avoid application when air or surface temperature is below 10°C or above 30°C and ensure that the product is not applied in direct sunlight.

Use of clear coats on benchtops

When used on Benchtops, Renovation Range Tiles and Benchtops MUST be overcoated with a Renovation Range Clear Coat. The Renovation Range Clear coats have been designed specifically to use over Renovation Range products, excluding the floors products. They are not recommended to be used as a primary coat direct onto a substrate. Renovation Range Clear Satin must not be applied over the top of Renovation Range Floors as this will reduce slip resistance of the Floors coating.

Adherence to minimum recoat times

Ensure that minimum recoat times are rigidly followed. Early recoat will result in gloss reduction. Mask up areas not requiring coating with a good quality masking tape. Take care to cover all areas as it will be difficult to remove paint once cured.

Return to use



Light use after 2 days (do not leave any objects sitting on the surface – take care not to expose to water or detergent).

Medium use after 3 days (can clean with mild detergent and water).

General use after 7 days (placement of objects on the surface).

Performance Guide

Weather Designed for interior use only. Not recommended for exterior use.	Salt Resistant against salt
Heat Resistance Upper heat resistance of 80°C.	Water Resistant against water.
Solvent Sensitive to aromatic hydrocarbons and alcohols.	Abrasion Good wet and dry burnish resistance and stain resistance.
Acid Resistant against mild acids.	Alkali Resistant against mild alkalis.

Typical Properties			
Gloss Level Satin		Thinner DO NOT THIN	
Colour Colourless			
Components 2		Number of Coats 2	
Toxicity Lead free. Dry film is non-toxic		V.O.C. Level < 101 g/L	
Shelf Life 2 years		Meets ECNZ V.O.C. Requirements? No	
Sanding Properties Good sandability		Mixing Ratio 50:1	
Pot Life 10 days		Touch Dry 30 minutes	
Clean Up  Water			
Clean Up Description Clean all equipment with water while wet. Do not attempt to recover dried out brushes or rollers.			
Application Methods  Air Spray  Airless Spray  Brush  Roller			
Application Conditions		Solids by Volume	
		<input type="text" value="35"/>	
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="83"/>	<input type="text" value="83"/>	<input type="text" value="83"/>
Dry Film Per Coat (microns)	<input type="text" value="29"/>	<input type="text" value="29"/>	<input type="text" value="29"/>
Recoat Time (min/hours)	<input type="text" value="480"/>	<input type="text" value="Indefinite"/>	<input type="text" value="480"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="12.07"/>	<input type="text" value="12.07"/>	<input type="text" value="12.07"/>

Application Guide

Surface Preparation

Surfaces previously painted with renovation range (excluding floors products)

If previously painted surfaces are dirty, wipe down with Selleys® Sugar Soap and rinse with clean water to remove any dirt, oil or grease.

If applying a clear coat to a surface recently painted with Renovation Range then lightly wiping with a wet rag to removed any dust will suffice.

Mask using a good quality painters tape

Application Procedure and Equipment

Add all of the Additive found underneath the blue lid to the paint. Stir well for approximately 2-5 minutes with a broad flat paddle, using an up and down scooping action until the additive is completely mixed into the paint. Once mixed the product is suitable to use for up to 10 days.

Application

Brush, Roller, conventional spray or airless spray application.

Stir thoroughly before and during use

1. Cut in as necessary using a 38-50mm high quality angled Sash Cutter brush.
2. Coat surface using a 4mm nap 100mm wide microfibre roller.
3. Lay off. Once each section is coated, gently go over the surface in the same direction with an unloaded roller using minimal pressure. This will give a smooth consistent finish. Using poor quality or worn rollers can affect the final finish achieved
4. Apply second coat of Renovation Range Clear after 8 hours for extra protection

Health and Safety

SDS Number

DLXGHSEN003237

SDS Link

[View SDS Link](#)

Using Safety Precautions

Keep out of reach of children.

Keep windows and doors open during use and while drying.

Wear overalls, safety glasses and impervious gloves. Use with adequate ventilation. If inhalation risk exists wear organic vapour/particulate respirator meeting the requirements of AS/NZS 1715 and AS/NZS 1716.

Available information suggests that gloves made from nitrile rubber should be suitable for intermittent contact. However, due to variations in glove construction and local conditions, the user should make a final assessment. Always wash hands before smoking, eating, drinking or using the toilet. Wash contaminated clothing and other protective equipment before storing or re-using.

Please refer to SDS Link. In case of emergency, please call 0800 220 770.

Transport and Storage	
Pack A 1	
Size: 1 LITRE	Weight: 1.20 KG
Flash Point NOT APPLICABLE - WATER BASED	UN Number NOT APPLICABLE
Dangerous Goods Class Not classified as dangerous goods	Package Group Not classified as dangerous goods
Pack B 1	
Size: 0.020 L	Weight: 0.032 KG
Flash Point Not applicable	UN Number Not applicable
Dangerous Goods Class Not classified as dangerous goods	

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.co.nz. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.