

NZPC00071 Dulux Protective Coatings Metalshield Cold Galv Primer

Description and Image

Previously known as Dulux Metalshiel Cold Galv. **Primer Dulux Metalshield® Cold Galv Primer** is an anti-corrosive zinc rich primer. The key components in Dulux Metalshield® Cold Galv Primer are anti-corrosive pigment (finely divided zinc dust) and chemical resistant resin.



Features and Benefits

- Zinc Rich
- Single pack
- Fast drying
- Surface tolerant
- Excellent galvanic protection for steel
- Convenience in use, reseal can for future use, minimal wastage
- Can be put into service or overcoated quickly
- Performs well on hand or power tool cleaned steel

Uses

Dulux Metalshield® Cold Galv Primer incorporates a high level of finely divided zinc in the dry film providing sacrificial protection to steel substrates with the convenience of one pack application. It is excellent for the repair of damaged galvanised steel and wrought iron balustrades and railings.

Performance Guide

<p>Weather Good resistance to weathering. Overcoat with suitable topcoat for maximum UV resistance</p>	<p>Salt Unaffected by splash and spillage of neutral salt solutions only.</p>
<p>Heat Resistance Up to 65°C dry heat.</p>	<p>Water Resists rain and condensation. Not recommended for permanently damp or immersed exposure.</p>
<p>Solvent Resistant to splash and spillage of aliphatic hydrocarbon solvents only.</p>	<p>Abrasion Good when fully cured.</p>
<p>Acid Not suitable for acidic conditions below pH 6</p>	<p>Alkali Not recommended for use in highly alkaline conditions</p>

Typical Properties

Finish
Flat

Colour
Grey

Components
1

Shelf Life
1 year minimum at 25°C

Thinner
DULUX CR Reducer

Line/Shade
812-87306

Application Methods

 **Air Spray**
 **Airless Spray**
 **Brush**
 **Roller**

Application Conditions

	Min	Max
Air Temperature	<input type="text" value="5"/>	<input type="text" value="40"/>
Substrate Surface Temperature	<input type="text" value="5"/>	<input type="text" value="40"/>
Relative Humidity	<input type="text"/>	<input type="text" value="85"/>

	Solids by Volume		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="119"/>	<input type="text" value="215"/>	<input type="text" value="180"/>
Dry Film Per Coat (microns)	<input type="text" value="50"/>	<input type="text" value="90"/>	<input type="text" value="75"/>
Recoat Time (min/hours)	<input type="text" value="3 hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="8.4"/>	<input type="text" value="4.7"/>	<input type="text" value="5.6"/>

Hardener Details

Surface Preparation

Steel:

Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Rust, millscale, oxide deposits and old paint films on metal surfaces must be removed by abrasive blast cleaning to AS1627.4 Class 2.5. Remove all dust by brushing or vacuum cleaning.

Galvanised steel:

Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Rust, millscale, oxide deposits and old paint films on metal surfaces should be removed by hand (AS1627.7 Class 2) or power tool (AS1627.2. Class 2) cleaning as a minimum. Coating performance is proportional to the degree of surface preparation and abrasive blast cleaning to a minimum AS1627.4 Class 2 is preferred for more severe environments. Remove all dust by brushing or vacuum cleaning.

Overcoating:

Aged coating should be tested for lifting by a method suitable to the coating thickness, for example 'X' cut or crosshatch methods. If it lifts, remove it. The surface must be free of oil, grease and other contaminants. Hand sand or high pressure water blast at 1,200 - 1,500 p.s.i. to remove loosely adhering chalk and dust prior to painting.

Application Guide

Application Method

Stir contents of each can thoroughly with a broad flat stirrer using a stirring, lifting action or use a power mixer. Remix thoroughly before using and continue mixing during application.

BRUSH/ROLLER: For small areas only. Apply even coats of the mixed material to the prepared surface. Thin if necessary with up to 100 ml/litre with DULUX CR Reducer to ease application. When brushing and rolling additional coats may be required to attain the specified thickness.

CONVENTIONAL SPRAY: Thin up to 200 ml/litre with DULUX CR Reducer to aid atomisation. Apply using an agitated pressure pot.

TYPICAL SET-UP:

De Vilbiss JGA 502 Gun: 704 Air Cap, E Fluid Tip, DEX Needle

Iwata W70 Gun: 021 Air Cap, 021 Fluid Needle, 021 Fluid Nozzle

Pressure at Pot: 70-100 kPa (10-15 p.s.i.)

Pressure at Gun: 380-410 kPa (55-60 p.s.i.)

AIRLESS SPRAY: Standard airless spray equipment such as Graco, Binks or others using a 40:1 or 45:1 pump ratio with a fluid tip of 19-21 thou (0.48-0.53mm) at a tip pressure of 13.8-20.6 MPa (2,000-3,000 p.s.i.). Keep pot agitated during spraying. Thinning is not normally required but up to 60 ml/litre of DULUX CR Reducer may be added to ease application.

Brush, roller, conventional or airless spray.

Precautions

Do not apply at temperatures below 5°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Do not topcoat with two pack products or products of a saponifiable nature such as alkyds.

Clean Up

Clean up thinner

Clean all equipment with DULUX CR Reducer.

Health and Safety	
Storage	Storage: Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
Handling	Handling: As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
Using	Using: Use with good ventilation and avoid inhalation of spray mists and fumes.
Flammability	Flammability: This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE.
Welding	Welding: Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.
In case of emergency, please call 1800 220 770.	

Transport and Storage	
Class 3	UN Number 1263

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.co.nz. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.